技术数据表 n° SIL 13 0013– 2013.01

BLUESIL™ EMUL 269

防水剂

概述	BLUESIL EMUL 269 是一款含氢硅油的水性乳液
应用举例	• 石膏、灰泥的防水添加剂 • 用于灰泥板或其它灰泥产品的制作过程 • 羟基硅油的交联剂 • 有机硅弹性体用于橡胶和其它极性表面的交联促进剂 纤维或矿物填料的处理剂
优点	• 对各种织物具有优异的防水性 • 当使用合适的催化剂，赋予织物持久的防水性 • 改善织物的撕裂强度
特性	• 外观..... 乳白色液体 • 颜色..... 白色 • 比重，25°C，约..... 1.0 • 固含量，%，约 ..... 50 • pH，约 ..... 3.5 • 溶剂.....无 • 稀释剂 .....水
工艺	用于灰泥中，建议将 BLUESIL EMUL 269 加入到水中。 **灰泥板** 相对于灰泥粉 0.3%-0.8%的 BLUESIL EMUL 269 添加量赋予产品优异的防水性能。 防水性能随着灰泥等级，灰泥与水的比率和添加剂的变化而变化。有时，灰泥的流变性能可能会改变，使用前请预先测试。 **浸轧工艺的织物后整理** BLUESIL EMUL 269易于用水稀释，如果使用SILCOLEASE EMUL 70827A作为催化剂，请将催化剂的稀释液加入到BLUESIL EMUL 269的稀释液中。 作为织物防水剂，建议的有机硅添加量为织物重的 0.5%-2.0%。

BLUESTAR SILICONES Delivering your potential.

BLUESIL™ EMUL 269

催化剂SILCOLEASE EMUL 70827A 的添加量为BLUESIL EMUL 269的20%，可以达到优异和持久的防水性能。

建议使用前预先测试，以选择最好的使用量。

请参阅宣传册“SiH 产品的安全使用

包装	具有呼吸阀的 1000kg 容器。
储存与保存期限	在+2℃到 30℃之间，保存在原包装中，BLUESIL EMUL 269 自包装上表明的生产日期起保存期 12 月。 超过保质期后,蓝星有机硅将不再保证产品达到销售的指标。
安全	请参考 BLUESIL EMUL 269 的安全数据表(MSDS)。

蓝星有机硅（上海）有限公司
上海市莘庄工业区金都路 3966 号
电话：+86 (021) 5442 6600

Visit our website www.bluestarsilicones.com

EUROPE
Bluestar Silicones France
21 Avenue Georges Pompidou
F69486 Lyon Cedex 03
FRANCE
Tel. (33) 4 72 13 19 00
Fax (33) 4 72 13 19 88

NORTH AMERICA
Bluestar Silicones USA
2 Tower Center Boulevard
Suite 1601
East Brunswick, NJ 08816-1100
United States
Tel. (1) 732 227-2060
Fax. (1) 732 249-7000

LATIN AMERICA
Bluestar Silicones Brazil Ltda.
Av. Maria Coelho Aguiar, 215
Bloco G – 1°andar
05804-902-Sao Paulo – SP-
Brazil
Tel. (55) 11 37477887

ASIA PACIFIC
Bluestar Silicones Hong Kong
Trading Co. Ltd
29th Floor, 88 Hing Fat Street
Causeway Bay
Hong Kong
Tel. (852) 3106 8200
Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.